

DERWENT ABSTRACT FOR: **JP 04-028739** (Mitsubishi), published 31 Jan 1992:

L1 ANSWER 3 OF 9 WPINDEX COPYRIGHT 2001 DERWENT INFORMATION LTD

ACCESSION NUMBER: 1992-085006 [11] WPINDEX

DOC. NO. CPI C1992-039266

TITLE: Thermoplastic resin compsn. prepn. - by blending polyolefin resin, polyphenylene ether resin and polymer having alkenyl aromatic and aliphatic hydrocarbon polymer chain.

DERWENT CLASS A12 A17 A25

PATENT ASSIGNEE(S): (MITF) MITSUBISHI PETROCHEMICAL CO LTD; (TOYT) TOYOTA JILOSHA KK

COUNTRY COUNT 1

PATENT INFORMATION:

PATENT NO	KIND	DATE	WEEK	LA	PG
JP 04028739	A	19920131 (199211)*		11	<--

APPLICATION DETAILS:

PATENT NO	KIND	APPLICATION	DATE
JP 04028739	A	JP 1990-133749	19900525

PRIORITY APPLN. INFO: JP 1990-133749 19900525

AN 1992-085006 [11] WPINDEX

AB JP 04028739 A UPAB: 19931006

Compsn is prepd. by blending component (B) and 20% or more of component (C) to obtain a compsn. (I), and then blending (I) with component (A) and the remaining (C). (A) is polyolefin resin 30-78 wt.%, (B) is polyphenylene-ether resin 20-63 wt.% and (C) is 2-50 wt.% polymer having both alkenyl aromatic cpd. polymer chain (C1) and aliphatic hydrocarbon polymer chain (C2) per molecule and dynamic shearing modulus at 23 deg.C of 3×10^8 dyne/cm² or higher.

(A) is isotactic polypropylene. (C) is partially hydrogenated alkenyl cpd.-conjugated diene block copolymer such as hydrogenated styrene-butadiene triblock copolymer.

ADVANTAGE - Compsn. has good mechanical properties, esp. a good balance between impact strength and rigidity.

2/0